

CONSTRUCTION Tufting 1/10" textured loop
STRUCTURE Tufté 1/10" bouclé
STRUKTUR Getuftet 1/10" Schlinge
STRUCTUUR Getuft 1/10" lussenpool

PERMANENTLY ANTISTATIC ISO 6356
ANTISTATIC PERMANENT < 2 kV
PERMANENT ANTISTATISCH
PERMANENT ANTISTATISCH

PILE MATERIAL 100% PA solution dyed
COMPOSITION DU VELOURS
POLMATERIAL
POOLMATERIAAL

IMPACT NOISE RATING ISO 140-8
ISOLATION PHONIQUE 24 dB ΔLw
TRITTSCHALLVERBESSERUNG
GELUIDSISOLATIE

PRIMARY BACKING Non woven PES
SUPPORT Non tissé PES
TRÄGERMATERIAL Vlies, PES
TUFTDOEK Vilt, PES

SOUND ABSORPTION ISO 354
ABSORPTION PHONIQUE 0.15 αw
SCHALLABSORPTIONSGRAD
GELUIDSABSORPTIE

SECONDARY BACKING Action Back
DOSSIER
RÜCKEN
TAPIJTRUG

THERMAL RESISTANCE ISO 8302
RÉSISTANCE THERMIQUE 0.073 m² K/W
WÄRMEDURCHLASSWIDERSTAND
WARMTEDOORLAATWEERSTAND

PILE WEIGHT Ca. 640 gr/m²
POIDS DU VELOURS
POLEINSATZGEWICHT
POOLGEWICHT

FASTNESS TO LIGHT ISO 105-B02
SOLIDITÉ A LA LUMIÈRE ≥ 7
LICHTECHTHEID
LICHTECHTHEID

TOTAL WEIGHT Ca. 2.050 gr/m²
POIDS TOTAL
GESAMTGEWICHT
TOTAAL GEWICHT

COLOUR FASTNESS TO WATER EN ISO 105-E01
SOLIDITÉ À L'EAU ≥ 4-5
WASSERRECHTHEID
WATERECHTHEID

PILE HEIGHT Ca. 2,8 mm
EPAISSEUR DU VELOURS
POLHÖHE
POOLHOOGTE

RUBBING FASTNESS EN ISO 105-X12
SOLIDITÉ AU FROTTEMENT ≥ 4
REIBECHTHEID
WRIJFECHTHEID

TOTAL HEIGHT Ca. 6 mm
EPAISSEUR TOTALE
GESAMTHÖHE
TOTALE DIKTE

FIRE RESISTANCE EN 13501-1
COMPORTEMENT AU FEU Cfl-s1
BRENNVERHALTEN
BRANDGEDRAG

TUFT DENSITY Ca. 140 000/m²
NOMBRES DE POINTS
NOPPENZAHL
AANTAL PUNTEN

NUMBER OF COLOURS 10
NOMBRES DE COULEURS
ANZAHL FARBEN
AANTAL KLEUREN


PILE DENSITY Ca. 0.125 g/cm³
DENSITÉ DU VELOURS
POLROHDICHTHEIT
POOLDICHTHEID

WIDTH EN ISO 3018
LARGEUR ca. 400 cm
BREITE
BREEDTE


CLASSIFICATION EN 1307
CLASSEMENT 33 - LC1
KLASSIFIKATION
CLASSIFICATIE


CASTOR CHAIR SUITABILITY EN 985
CHAISE À ROULETTES A: intensive use
STUHLROLLENEIGNUNG
ROLSTOELGESCHIKTHEID

STAIR SUITABILITY EN 1963
ESCALIERS A: intensive use
TREPPENEIGNUNG
TRAPPENGESCHIKTHEID




REG. NR
C42EE342
www.pro-dis.info







▲ 98




▲ 96




▲ 97



▲ 93




▲ 90



▲ 78



▲ 72



▲ 12



▲ 47



▲ 32