


Strong 745 S-L

Manufacturing process	Needlefelt		ISO 2424
Type of surface	Flecked		
Surface aspect	Coarse Fibred		ISO 2424
Width	200 cm		
Backing	LV		ISO 2424
Pile yarn composition	100% dorix® PA		
Pile weight	650 g/m ²		
Total weight	1450 g/m ²	+/- 10%	ISO 8543
Total height	6,5 mm	+/- 10%	ISO 1765
Overall use class	Commercial 33, Areas with heavy use		EN 1307
Luxury class	LC1		EN 1307
Castor chair suitability	Yes, permanent use		EN 985
Stair suitability	Yes, permanent use		EN 1307
Colour fastness to light	≥ 5		ISO 105-B02
Colour fastness to rubbing, wet and dry	≥ 4		ISO 105-X12
Colour fastness to water	≥ 4		ISO 105-E01
Dimensional stability	Shrinkage ≤ 1,2 %		ISO 2551
	Extension ≤ 0,5 %		ISO 2551
Electrostatic charging	< 2kV		ISO 6356
Vertical resistance	< 1,0x10 ⁸ Ω		ISO 10965
Thermal resistance	0,11 m ² .K/W		ISO 8302
Slip resistance	> 0,3	Machine direction	EN 13893
	> 0,3	Crossdirection	EN 13893
Flammability	Bfl,s1 (Glued)		EN 13501-1

Floorsymbols



Certificates



dorix®

